



## TITAN Fast Sealer

TITAN Fast Sealer is an economical, single pack, fast drying sealer designed to be used as a first coat over raw timber and cork flooring.

---

### Advantages

- Fast drying
- Easy sanding

---

### Typical Applications

Interior use only. Timber, parquetry, particleboard or cork flooring.

*Not suitable for exterior or wet area applications e.g. bathrooms or around swimming pools.  
Caution: floor will be slippery when wet.*

---

### Coverage

<b>Basecoat:</b>	Timber & Parquetry	12-15 m <sup>2</sup> per litre
	Cork & Particleboard	Coverage will be reduced

Coverage is dependent upon the porosity of the substrate.

---

### Application Method

By roller and a high quality brush.

- Roller                                      6mm mohair roller.
- Brush

---

### Thinning

Not normally required but, if desired, add up to 5% Thinners 3310 or in hot weather add up to 3% Wet Edge Extender 3320.

---

### Dry Time

30-60 minutes.

Low temperatures and heavy film thickness will retard drying times. Direct sunlight and draft during drying may affect the final gloss level of the coating.

---

### Application

Preparing the floor to a professional standard is essential to achieve the best results.

# TITAN Fast Sealer

Economical, single pack, fast drying sealer.



## Preparation:

- Fill all nail holes with a water based putty, allow to dry.
- Sand uncoated floor with 120-150 grade sandpaper or screenback on a flexible pad to ensure floor is uniformly dull with no sanding scratches, nibs or fur. Vacuum thoroughly to ensure all sanding dust is removed. Take care to avoid scratching the surface.
- Apply a liberal first coat of TITAN Fast Sealer using a 6mm mohair roller and good quality brush to cut in. Allow to dry for 45 minutes.
- Sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Vacuum all dust.
- Apply a coat of TITAN Gloss. Allow to dry per instructions on the data sheet.
- Thoroughly sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Vacuum all dust.
- Apply the final coat of TITAN Gloss (per data sheet directions).

*Note: Only pour sufficient coating to complete the job, replace the lid immediately as exposure to the environment can cause the product quality and performance to be affected. Ensure all opened cans are used within one week. Do not return unused product to the can as this will cause the remaining material to increase in viscosity.*

## Recommended Topcoats

TITAN Gloss.

<b>Properties</b>	<b>Colour</b>	Milky in can, dries clear.
	<b>Finish</b>	Sealer
	<b>Build</b>	Good
	<b>Sandability</b>	Excellent
	<b>Levelling &amp; Flow</b>	Excellent
	<b>Pack Sizes</b>	20L
	<b>Product Code</b>	3510-20
	<b>Clean Up</b>	Polycure Super Cleaning Solvent 3300. Ensure all cleaning solvents are removed before placing back in the coating.
	<b>Shelf Life</b>	24 months, see label for use by date. (store in sealed container below 25°C). Do not use product past use by date.

## Refer to the TITAN Product Information Guide for more information

Note: All coatings provide protection for the timber or substrate. However, no coating is indestructible and all coatings will mark or scratch depending upon what comes into contact with the coating. Sharp objects including sand and grit will scratch the surface of any coated floor regardless of coating type. In high traffic commercial environments such as hair dressing salons, night clubs and taverns many factors need to be considered when choosing a coating system. Refer to the Product Information Guides for further information.

# TITAN Fast Sealer

Economical, single pack, fast drying sealer.

---



## Health & Safety

Before handling, refer to the Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated SDS and packaging label before using this product.

Note: Coatings give off strong solvents and odours during the drying process. People and pets should be removed from the building during the application and drying of coatings. All food and fabrics should also be removed to reduce the risk of them becoming tainted during the drying process.

---

ABN 40 000 041 136  
21 Marigold Street, Revesby NSW 2212, Australia, P +61 2 9795 3700 F +61 2 9771 3601  
[sales@mirotone.com.au](mailto:sales@mirotone.com.au)

[www.polycure.com.au](http://www.polycure.com.au)